

SeaRox® SL 340

SeaRox SL 340 is a semi-rigid stone wool insulation slab (board). Reinforced aluminium foil (ALU), black tissue (TB) and glass cloth facings (GW200, GW400, GW-A, ALU-G) facings are available upon request.



Application

The slab (board) is suitable for acoustic insulation of bulkheads and decks.

Product properties


Product property	Performance		Norms
Thermal conductivity	T (°C) λ (W/mK)	10 0,035	EN 12667
Maximum service temperature	250 °C		EN 14706
Advised maximum surface temp. for facings	80 °C		
Nominal density	80 kg/m ³		EN 1602
Fire classification	Non-combustible Low flame spread characteristics (for facings)		IMO 2010 FTP Code
Water absorption	≤ 1 kg/m ²		EN 1609 EN ISO 29767
Sound absorption (directly mounted)	Thickness: 50 mm unfaced $\alpha_w = 0,9$ Thickness: 2x50 mm unfaced $\alpha_w = 0,95$		ISO 354 Evaluated after ISO 11 654

Compliance

- SeaRox SL 340 complies to directive 2014/90/EU of 23 July on marine equipment (MED) and IMO 2010 FTP Code.
- Above product declarations are also applicable for product with optional facing.
- ROCKWOOL stone wool insulation is made from volcanic rock and complies with Note Q, regulation (EC) No. 1272/200.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL A/S and cannot be used without a prior written consent.



0575



0097