



ProRox® SL 930NA

ProRox SL 930 is a semi-rigid stone wool thermal insulation board for intermediate to high temperature industrial applications.

Application

The board is suitable for the thermal and acoustic insulation of horizontal and vertical applications requiring a stable insulation product, such as tank walls, vessels and columns.



Product properties in accordance with ASTM C6121)

Property	Performance							Test standard
Thermal conductivity	T _m (°F)	100	200	300	400	500	600	- ASTM C177
	λ (BTU.in/hr.ft ² .°F)	0.27	0.33	0.41	0.51	0.63	0.78	
	T _m (°C)	38	93	150	204	260	316	
	λ (W/mK)	0.038	0.047	0.059	0.074	0.092	0.116	
Maximum use temperature	1200°F (650°C)							ASTM C411 / C447
Linear shrinkage	≤ 2% at 1200°F (650°C)							ASTM C356
Reaction to fire	Flame spread index = 0							ASTM E84
	Smoke development = 0							UL723 / CAN ULC 102
Corrosion resistance	Stress corrosion cracking tendency of austenitic stainless steel = passed Chemical analysis (Cl $^{-}$, Fl $^{-}$, Na $^{+}$, SiO $_{4}^{-4}$): results fall within acceptability limits of ASTM C795							ASTM C692 / C795 ASTM C871 / C795
Water absorption	$\leq 0.2 \text{ lb/ft}^2 (\leq 1.0 \text{ kg/m}^2)$							EN 1609 / ISO 29767
Vapor sorption	< 1% Weight							ASTM C1104
Density ²⁾	Nominal density 4.0 lb/ft³ (64kg/m³), Actual density 3.5 lb/ft³ (56 kg/m³)							ASTM C303

¹⁾ All values are nominal values for standard industrial production. Standard industrial production tolerances applicable.

Compliance

- ProRox SL 930 fully complies with the requirements as set by internationally reconginzed standards like ASTM C612 type IVA.
- ROCKWOOL stone wool insulation is made from volcanic rock and is not classified as a hazardous substance in accordance with Note Q, regulation (EC) No. 1272/2008.





Disclaimer

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL A/S and cannot be used without a prior written consent.

²⁾ Density is not a performance criteria but is commonly referred to when specifying insulation. Actual density is the true density of the insulation and nominal density is the effective density of the insulation relative to a historic benchmark where the insulation contained 40% non-fibrous content also known as shot (ASTM C612-99).